

Amendments to the Specification

Please replace the paragraph beginning at page 11, line 3, with the following rewritten paragraph:

-- Airlaid -- The airlaid material was made from a 90/10 blend of NF405 pulp and Kosa T-255 conjugate fibers. The nonwoven web had a basis weight of 175 gsm and a density of ~~0.8~~ 0.08 gm/cc. Samples were cut from this web and were about 250 mm long, 60 mm wide, 2 mm in thickness and had a weight of about 2.75 grams. --